

Technical Data Sheet

Epolight™ 2066 Near Infrared Dye

DESCRIPTION

Excellent visible light transmission for a monovalent amminium dye

Contains no metals

Suitable for coatings

PROPERTIES


Absorption maximum, λ max: 978 nm Absorptivity in acetone: 82 L g⁻¹ cm⁻¹

Appearance: green powder Melting point: 98 - 100°C

Solubility in grams/100 grams of solvent:

MEK >6.0 grams Ethyl acetate 1.9 grams THF >6.0 grams

Cyclohexanone >6.0 grams Methyl pyrrolidinone 4.9 grams



Although the information in this data sheet is presented in good faith and believed to be correct, Epolin makes no representations or warranties as to the completeness or accuracy of the information which is supplied upon the condition that the persons receiving same will make their own determination as to its suitability for their purposes prior to use. In no event will Epolin be responsible for damages of any nature whatsoever resulting from the use of or reliance upon information from this data sheet or the products to which the information refers.

© Epolin All Rights Reserved rev 04/13