



# Technical Data Sheet

## Epilight™ 3138 Near Infrared Dye

---

### DESCRIPTION


Excellent thermal stability  
Excellent light stability  
Low solubility in most organic solvents  
Suitable for injection molding  
Contains Nickel

---

### PROPERTIES

Absorption maximum,  $\lambda$  max: 924 nm  
Absorptivity in chloroform: 50 L g<sup>-1</sup> cm<sup>-1</sup>  
Appearance: brown powder  
Melting point: 310 - 315°C  
Solubility in grams/100 grams of solvent:  
    MEK 0.22 grams  
    Xylene 2.24 grams  
    THF 4.49 grams  
    Cyclohexanone 1.61 grams

---



Although the information in this data sheet is presented in good faith and believed to be correct, Epolin makes no representations or warranties as to the completeness or accuracy of the information which is supplied upon the condition that the persons receiving same will make their own determination as to its suitability for their purposes prior to use. In no event will Epolin be responsible for damages of any nature whatsoever resulting from the use of or reliance upon information from this data sheet or the products to which the information refers.