

Technical Data Sheet

Epilight™ 5843 visible yellow dye

DESCRIPTION

Suitable for plastics

Excellent thermal stability

PROPERTIES

Absorption maximum, λ max: 444 nm

Absorptivity in chloroform: $137 \text{ L g}^{-1} \text{ cm}^{-1}$

Appearance: Yellow powder


Melting point: 115°C

Solubility in grams/100 grams of solvent:

Xylenes 15.4 grams

Acetone 25.3 grams

Methylene Chloride 41.7 grams



Although the information in this data sheet is presented in good faith and believed to be correct, Epolin makes no representations or warranties as to the completeness or accuracy of the information which is supplied upon the condition that the persons receiving same will make their own determination as to its suitability for their purposes prior to use. In no event will Epolin be responsible for damages of any nature whatsoever resulting from the use of or reliance upon information from this data sheet or the products to which the information refers.