

Technical Data Sheet

Epolight 5851 visible dye

DESCRIPTION

Narrow band visible absorber

Suitable for thermoplastic processing


PROPERTIES

Absorption maximum, λ max: 423 nm in chloroform; 426 nm in polycarbonate

Absorptivity in chloroform: $596 \text{ L g}^{-1} \text{ cm}^{-1}$

Appearance: purple powder

Absorbance spectrum Epolight 5851 in polycarbonate



Although the information in this data sheet is presented in good faith and believed to be correct, Epolin makes no representations or warranties as to the completeness or accuracy of the information which is supplied upon the condition that the persons receiving same will make their own determination as to its suitability for their purposes prior to use. In no event will Epolin be responsible for damages of any nature whatsoever resulting from the use of or reliance upon information from this data sheet or the products to which the information refers.