

Technical Data Sheet

Epilight™ 6084 Phthalocyanine Dye

DESCRIPTION

Excellent solubility in polycarbonate

Suitable for injection molding

Suitable for coatings

PROPERTIES

Absorption maximum, λ max: 695 nm


Absorptivity in chloroform: $90 \text{ L g}^{-1} \text{ cm}^{-1}$

Appearance: blue powder

Melting point: 190 - 195°C

Solubility in grams/100 grams of solvent:

Methanol 14 grams



Although the information in this data sheet is presented in good faith and believed to be correct, Epolin makes no representations or warranties as to the completeness or accuracy of the information which is supplied upon the condition that the persons receiving same will make their own determination as to its suitability for their purposes prior to use. In no event will Epolin be responsible for damages of any nature whatsoever resulting from the use of or reliance upon information from this data sheet or the products to which the information refers.