

Technical Data Sheet

Epolight™ 6860 dye

DESCRIPTION

IR absorber suitable for thermoplastic processing

Excellent thermal and solar stability

PROPERTIES


Absorption maximum, lambda max: 744 nm

Absorptivity in chloroform: 147 L g⁻¹ cm⁻¹

Appearance: green powder

Melting point: 290°C

absorbance spectrum of Epolight 6860 in chloroform



Although the information in this data sheet is presented in good faith and believed to be correct, Epolin makes no representations or warranties as to the completeness or accuracy of the information which is supplied upon the condition that the persons receiving same will make their own determination as to its suitability for their purposes prior to use. In no event will Epolin be responsible for damages of any nature whatsoever resulting from the use of or reliance upon information from this data sheet or the products to which the information refers.