



# Technical Data Sheet

## Epilight 7829 visible dye

---

### DESCRIPTION

Visible absorber suitable for thermoplastic processing

Provides orange lens color

Excellent thermal and solar stability

---

### PROPERTIES


Absorption maximum,  $\lambda$  max: 458 nm in polycarbonate

Melting point: 183-188°C

Solubility in grams/100 grams of solvent:

- MEK 4.4 grams
  - Xylene 6.2 grams
  - Toluene 8.8 grams
  - Acetone 2.4 grams
- 

absorbance spectrum of Epilight 7829 in polycarbonate



Although the information in this data sheet is presented in good faith and believed to be correct, Epolin makes no representations or warranties as to the completeness or accuracy of the information which is supplied upon the condition that the persons receiving same will make their own determination as to its suitability for their purposes prior to use. In no event will Epolin be responsible for damages of any nature whatsoever resulting from the use of or reliance upon information from this data sheet or the products to which the information refers.